



ASTM AGENT-LIST		5 MINUTES			24 HOURS		
		Surface Dulling	Surface Attack	Color Change	Surface Dulling	Surface Attack	Color Change
		5% Acetic Acid (White Vinegar)	0	0	0	0	0
5% Ammonia	0	0	0	0	0	0	
5% Hydrochloric Acid	0	0	0	0	0	0	
5% Phenol	0	0	0	0	0	0	
5% Sodium Hydroxide	0	0	0	0	0	0	
70% Isopropyl (Rubbing) Alcohol	0	0	0	0	0	0	
Bleach	0	0	0	0	0	0	
Gasoline	0	0	0	0	0	0	
Kerosene	0	0	0	0	0	0	
Mineral Oil	0	0	0	0	0	0	
Olive Oil	0	0	0	0	0	0	
Sulfuric Acid	0	0	0	0	0	0	

EXTENDED AGENT-LIST		5 MINUTES			24 HOURS		
		Surface Dulling	Surface Attack	Color Change	Surface Dulling	Surface Attack	Color Change
		A456 II Germicide	0	0	0	0	0
Acetone	0	0	0	0	0	0	
Aniline Blue	0	0	1	0	0	1	
Ball Point Pen	0	0	1	0	0	1	
Betadine	0	0	1	0	0	1	
Bicarbonate	0	0	0	0	0	0	
Bleach 10%	0	0	0	0	0	0	
Blood	0	0	0	0	0	0	
Cherry Soda	0	0	0	0	0	0	
Disinfectants: Phenolic/Quaternary	0	0	0	0	0	0	
Ecoshine Stainless Steel Polish	0	0	0	0	0	0	
Ethyl Alcohol	0	0	0	0	0	0	
Hematoxylin	0	0	0	0	0	0	
Iodine	0	0	1	0	0	1	
Lemon Eze	0	0	0	0	0	0	
Lime A Way	0	0	0	0	0	0	
Methylene Blue	0	0	1	0	0	1	
Mineral Spirits	0	0	0	0	0	0	
Permanent Marker	0	0	1	0	0	1	
Potassium Permanganate	0	0	2	0	0	2	
Purell® Hand Sanitizer	0	0	0	0	0	0	
QC 31 Neutral Cleaner	0	0	0	0	0	0	
QC 52 Glass Cleaner	0	0	0	0	0	0	
QC 53 General Purpose Cleaner	0	0	0	0	0	0	
Red Kool Aid	0	0	1	0	0	1	
Red Wine	0	0	0	0	0	0	
Shoe Polish Paste Brown	0	0	0	0	0	0	
Tar	0	0	0	0	0	0	
Yellow Mustard	0	0	0	0	0	0	

**KEY**  
 0 - No Change  
 1 - Slight Change  
 2 - Moderate Change  
 3 - Severe Change

**NOTES**  
 Tests were conducted per ASTM F925 and values recorded after durations of 5 minutes and 24 hours. Testing and reporting were conducted by an independent laboratory.